

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 October 2001 (11.10.2001)

PCT

(10) International Publication Number
WO 01/74944 A1

(51) International Patent Classification⁷: **C08L 51/04**,
55/02, 27/06, 33/08, C08F 265/04, 279/02, 263/04

(21) International Application Number: PCT/US01/08937

(22) International Filing Date: 20 March 2001 (20.03.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/538,648 30 March 2000 (30.03.2000) US

(71) Applicant: **BAYER CORPORATION** [US/US]; 100
Bayer Road, Pittsburgh, PA 15205-9741 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report

(72) Inventors: **CHEN, Chuan-Ju**; 95 Larkspur Drive,
Amherst, MA 01002 (US). **GAGE, Marc, E.**; 228 Barry
Street, Feeding Hills, MA 01030 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(74) Agents: **PREIS, Aron et al.**; Bayer Corporation, Patent
Department, 100 Bayer Road, Pittsburgh, PA 15205-9741
(US).



WO 01/74944 A1

(54) Title: THERMOPLASTIC MOLDING COMPOSITION HAVING IMPROVED DIMENSIONAL STABILITY AND LOW GLOSS

(57) Abstract: A thermoplastic molding composition which features improved dimensional stability and low gloss is disclosed. The composition which contains (A) a first grafted rubber having a weight average particle size of 0.05 to 0.30 microns, (B) a second grafted rubber having a weight average particle size of 0.31 to 1.00 microns, (C) vinyl chloride (co) polymer, and, optionally, (D) styrene copolymer, is especially suitable for extruding profiles. In a preferred embodiment, at least one of the grafted rubbers is characterized in that its substrate features a core-shell structure, wherein the core contain at least one crosslinked vinylaromatic polymer, and the shell is elastomeric.

**THERMOPLASTIC MOLDING COMPOSITION
HAVING IMPROVED DIMENSIONAL STABILITY AND LOW GLOSS**

The invention concerns a thermoplastic molding composition and more particularly a composition, which contains grafted rubber having a bimodal size distribution.

SUMMARY OF THE INVENTION

5 A thermoplastic molding composition which features improved dimensional stability and low gloss is disclosed. The composition which contains (A) a first grafted rubber having a weight average particle size of 0.05 to 0.30 microns, (B) a second grafted rubber having a weight average particle size of 0.31 to 1.00 microns, (C) vinyl chloride (co) polymer, and,
10 optionally, (D) styrene copolymer is especially suitable for extruding profiles. In a preferred embodiment, at least one of the grafted rubbers is characterized in that its substrate features a core-shell structure, wherein the core contain at least one crosslinked vinylaromatic polymer, and the shell is elastomeric.

15 **BACKGROUND OF THE INVENTION**

 It has long been known that thermoplastically processable styrene/acrylonitrile copolymers (SAN) may be imparted improved impact properties by the incorporation of rubbers. In ABS polymers, diene polymers are used as the rubbers for toughening, most notably at low
20 temperatures; however, the relatively poor weathering and aging resistance make these materials less favored in more demanding applications. In some such applications, use has successfully been made of crosslinked acrylic acid ester polymers; these are the well-known ASA copolymers. Such copolymers have been described in U.S. Patent
25 3,055,859 and in German Patents 1,260,135 and 1,911,882. Accordingly, the preferably crosslinked, rubbery acrylic acid ester polymer which serves as the grafting base (substrate) is first prepared by emulsion polymerization and the latex thus prepared is then grafted, preferably by emulsion, with a mixture of styrene and acrylonitrile. The art thus has long

- 2 -

recognized that improved impact strength, notched Izod and greater hardness are associated with ASA products which have, as a grafting base, a polyacrylate latex having a mean particle diameter of about 150 to 800 nm and a narrow particle size distribution. Also, noted is U.S. Patent 5 4,224,419 which disclosed an ASA based composition that contains two different graft copolymers of SAN onto crosslinked acrylates, and a hard copolymeric SAN component. U.S. Patent 5,157,076 is noted for its disclosure of a thermoplastic elastomer having improved abrasion resistance, the composition containing a (co)polymer of vinyl chloride and 10 ASA as an impact modifier.

The art refers to "hard" and "soft" segments in terms of the relative position of their glass transition temperature vis a vis room temperature. "Hard" means T_g above room temperature and "soft" means below room temperature. Multi-phase structured emulsion copolymers, including hard- 15 soft and hard morphologies have been disclosed in EP 534,212 and in the documents referenced therein. Accordingly, graft copolymers having a hard core of polystyrene, a first butyl acrylate shell and an outer SAN shell are known. Significantly, the '212 document disclosed a monomodal system containing particles having a styrene core and measuring less than 20 0.2 microns. Also presently relevant is U.S. Patent 5,932,655 that disclosed grafted rubbers having core/shell structures, the rubbers having bimodal size distribution, of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The inventive thermoplastic composition comprises:

- 25 (A) a first grafted rubber having a weight average particle size of 0.05 to 0.30, preferably 0.10 to 0.25 microns, and
- (B) a second grafted rubber having a weight average particle size of 0.31 to 1.00, preferably 0.32 to 0.60 microns, and
- (C) a (co)polymer of vinyl chloride, and optionally
- 30 (D) a styrene copolymer,

- 3 -

wherein rubber content is 15 to 25, preferably 17 to 23 percent relative to the total weight of (A), (B), (C) and (D).

Preferably the total amount of (A) and (B) is about 25 to 50 percent, the amount of (C) is about 25 to 75 percent and (D) may be present in a positive amount of up to 20 percent, the percents being relative to the total of A, B, C and D. Components A and B may be present at a weight ratio of 9/1 to 1/9 therebetween.

The grafted rubber, in both component (A) and (B), contains a grafted phase and a substrate, the weight ratio therebetween preferably ranges from 0.3 to 1, preferably 0.5 to 0.9. In the preferred embodiments, the substrate of at least one of (A) and (B) has a core-shell structure. The grafted phase contains a copolymer of at least one monomer selected from a first group consisting of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated styrene and at least one monomer selected from a second group consisting of (meth)acrylonitrile and methyl methacrylate. The weight ratio between said monomer(s) of said first group to said monomer(s) of said second group ranges between 80:20 to about 65:35.

The substrate of (A) and/or (B) comprises the crosslinked polymerization product of at least one member selected from the group consisting of C₂₋₈-alkyl acrylate, vinyl acetate, hydrogenated diene and diene. In a preferred embodiment, the substrate comprises a core/shell structure in at least one of (A) and (B). In these embodiments, the substrate contains about 2 to 40, preferably 5 to 30% relative to the weight of the substrate, of a core containing at least one, preferably crosslinked, vinylaromatic polymer, and about 60 to 98, preferably 70 to 95% relative to the weight of the substrate, of a shell containing the crosslinked polymerization product of at least one member selected from the group consisting of C₂₋₈-alkyl acrylate, vinyl acetate, hydrogenated diene and diene.

- 4 -

The (co)polymer of vinyl chloride, component (C) includes polyvinyl chloride homopolymer and vinyl chloride copolymers of at least one of: esters of vinyl alcohol containing 1 to 20 carbon atoms in the acid portion used to make the ester such as vinyl stearate, vinyl epoxystearate, vinyl benzoate, and vinyl acetate; acrylates and methacrylates containing 1 to 20, preferably 2 to 10 carbon atoms in the alcohol group that is used to make the ester such as ethyl acrylate, butyl acrylate, 2-ethylhexyl acrylate; acrylonitrile, methacrylonitrile, and derivatives thereof; esters of unsaturated dicarboxylic acids such as maleates, fumarates, and itaconates; carbon monoxide; olefins containing 2 to 20, preferably 2 to 6 carbon atoms such as ethylene, propylene and isobutylene; diolefins containing 4 to 20, preferably 4 to 8 carbon atoms such as butadiene, isoprene and halogen derivatives thereof such as chloroprene; alkyl vinyl ethers such as vinyl isobutyl ether and cetyl vinyl ether; vinyl aromatics containing 8 to 30, preferably 8 to 16 carbon atoms such as styrene, alpha-methyl styrene, and halogenated derivatives thereof such as para-chlorostyrene; vinyl organometallics such as monovinyl-diethyl tin laurate, trialkyl tin acrylate and methacrylate, trialkylvinyl tin, unsaturated trihydrocarbon phosphate esters, vinyl phosphonic acid, N-chlorophthalimide, poly-N-allyl substituted aminotriazine, N-substituted maleimide, vinyl pyridine, vinyl imidazole; alkenyl halides such as vinylidene chloride, vinyl bromide and fluoride, halogenated propenes, vinylidenechlorofluoride, dichloroethylene; allyl glycidyl ether; allyl esters of hydroxyalkanoic acids; dimethyl dicrotonate; chloroallydene; isopropenyl chloride; tetrafluoroethylene; norbornene acrylate; (cyanoethoxy) ethyl acrylate; and isopropenyl acetate.

PVC resins useful in the practice of this invention include copolymers of vinyl chloride containing up to 90 and preferably up to 70, and especially 30 to 60 weight percent of copolymerizable monomers. Methods for preparing the PVC polymers are also well known and such

- 5 -

resins are widely available commercially in a variety of molding and extrusion grades.

The optional styrene copolymer, component (D) contains a copolymer of at least one monomer selected from a first group consisting of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated
5 styrene and at least one monomer selected from a second group consisting of (meth)acrylonitrile and methyl methacrylate. The weight ratio between said monomer(s) of said first group to said monomer(s) of said second group ranges from 80:20 to about 65:35.

10 The grafted rubbers, components (A) and (B) of the inventive composition, may be prepared by graft copolymerization of at least one of styrene, α -methyl styrene, ring halogenated styrene, ring-alkylated styrene, such as p-methylstyrene and tert.butylstyrene with at least one of (meth)acrylonitrile and methylmethacrylate in the presence of the
15 substrate. Since 100% grafting yield cannot be achieved in the graft copolymerization, the polymerization product from the graft copolymerization always contains a proportion of free, non-grafted copolymer (for convenience, the grafted phase is referred to hereinafter in this text as SAN). However, for the purposes of the present invention, the
20 term "grafted rubber" is only applied to the rubber to which SAN have actually been grafted. The proportion of the grafted SAN in the polymerization product from the graft copolymerization can be determined in the conventional manner by extracting the free, non-grafted SAN
25 copolymer from the polymerization product, for example by methyl ethyl ketone. The principles of the method of separation have been described by Moore, Moyer and Frazer, Appl. Polymer Symposia No. 7, page 67 et seq. (1968).

The degree of grafting, in the present context, refers to the percentage proportion, based on the total graft rubber, of the SAN, which
30 is chemically bonded in the grafting branches of the graft copolymer. The

- 6 -

degree of grafting may be calculated from the analytically determined composition of the gel, which is insoluble in methyl ethyl ketone.

The particle size according to the invention is the weight-average particle size as determined by an ultracentrifuge, such as in accordance
5 with the method of W. Scholtan and H. Lange, *Kolloid-Z. und Z.-Polymere* 250 (1972), 782-796. The ultracentrifuge measurement gives the integral mass distribution of the particle diameters of a sample. From this, it is possible to determine that the percentage by weight of the particles have a diameter equal to or less than a certain size.

10 The graft rubber useful according to the invention, namely component (A) and (B), may be prepared in the conventional manner by methods that are well known in the art. The preferably crosslinked core, which is present in at least one of (A) and (B) of the preferred
15 embodiments, may be prepared by conventional emulsion techniques which are well known in the art. The monomers to be employed are at least one member selected from the group consisting of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated styrene, such as p-methylstyrene and tert.butylstyrene. Crosslinking may be attained by the incorporation of small amounts, usually about 0.5 to 10%, preferably 0.5 to
20 3%, relative to the weight of the core, of any of the polyfunctional monomeric cross-linking agents, which are well known in the art. Examples include tri allyl cyanurate, di allyl maleate and di vinyl benzene.

The substrate or the shell in the relevant embodiments that entail substrate having core/shell structures, in components (A) and (B) contains
25 the crosslinked polymerization product of at least one member selected from the group consisting of C_{2-8} -alkyl acrylate, vinyl acetate, hydrogenated diene and diene.

In the relevant preferred embodiment, the shell contains an acrylic acid ester polymer having a glass transition temperature of below 0°C.
30 Preferably, this temperature should be below -20°C., more particularly

- 7 -

below -30°C. The glass transition temperature of the polymer making up the shell may be determined by the DC method (K. H. Illers, Makromol. Chemie 127 (1969), page 1). Suitable alkyl acrylates for the preparation of acrylic acid ester polymers are those where the alkyl has 2 to 8 carbon atoms, most preferably those where the alkyl has 4 to 8 carbon atoms. Specific examples are n-butyl acrylate and ethylhexyl acrylate. The acrylic acid esters may be employed as individual compounds or as mixtures with one another. In the preparation of the core-shell phases, the monomers making up the shell are polymerized in the presence of the previously prepared core polymer.

In order to obtain crosslinking of the preferred acrylic polymers, the polymerization is preferably carried out in the presence of from 0.5 to 10% by weight, preferably from 0.5 to 3% by weight, based on the total monomers employed for the preparation of the grafting bases, of a copolymerizable, polyfunctional, preferably trifunctional, monomer which effects crosslinking and subsequent grafting. Suitable bifunctional or polyfunctional crosslinking monomers are those which contain two or more, preferably three, ethylenic double bonds which are capable of copolymerization and are not conjugated in the 1,3-positions. Examples of suitable crosslinking monomers are divinylbenzene, diallyl maleate, diallyl fumarate and diallyl phthalate, triallyl cyanurate and triallyl isocyanurate. Grafting agents may optionally be included, including unsaturated monomers having epoxy, hydroxy, carboxyl, amino or acid anhydride groups, for example, hydroxyalkyl (meth)acrylates.

The preparation of the preferred core/shell-structured grafted rubbers, (A) and/or (B), to be employed according to the preferred embodiment of invention, may be carried out in accordance with the following method. The preferably crosslinked vinyl aromatic core is first prepared by polymerizing the vinyl aromatic monomer(s) in aqueous emulsion by conventional methods at from 20 to 100°C, preferably from 50

- 8 -

to 90°C. The conventional emulsifiers, for example, alkali metal salts of alkyl sulfonic acids or alkyl aryl sulfonic acids, alkyl sulfates, fatty alcohol sulfonates, salts of higher fatty acids of 10 to 30 carbon atoms, or rosin soaps, may be used. The sodium salts of alkyl sulfonic acids or the

5 sodium salts of fatty acids of from 10 to 18 carbon atoms are preferred. Advantageously, the emulsifier is used in an amount of from 0 to 5% by weight, especially from 0 to 2% by weight, based on the monomer(s) employed to prepare the core polymer. In general, a water:monomer ratio of from 50:1 to 0.7:1 is used. The polymerization initiators used are, in

10 particular, the conventional persulfates, e.g., potassium persulfate, but redox systems can also be employed. In general, the initiator is used in an amount of from 0.1 to 1% by weight, based on the monomer(s) employed in the preparation of the core. Further polymerization additives which may be employed are the conventional buffers, to bring the pH to about 6 to 9,

15 for example, sodium bicarbonate and sodium pyrophosphate, and from 0 to 3% by weight of a molecular weight regulator, for example, a mercaptan, terpinol, or dimeric α -methyl styrene.

The precise polymerization conditions, such as the nature, rate of addition, and amount of the emulsifier initiator, and other additives, are

20 selected, within the ranges referred to above, so that the resulting latex of the preferably crosslinked vinyl aromatic core polymer attains the indicated particle size. The particle size distribution of the particles making up the core in each of (A) and in (B) is monomodal. In the inventive composition, the particles of (A) and (B) conform to a bimodal size distribution.

25 The crosslinked elastomeric substrate, that in the preferred embodiments form the shell of (A) and/or (B) is preferably prepared by polymerizing at least one member selected from the group consisting of C₂₋₈-alkyl acrylates and butadienes in the known emulsion polymerization process. In the formation of a core/shell substrate, this polymerization is

30 carried out in the presence of the previously prepared core latex as

- 9 -

described above. In the relevant embodiments, the elastomeric shell amounts to about 60 to 98, preferably 70 to 95 percent relative to the total weight of the core-shell phase. A conventional aqueous emulsion polymerization process at temperatures of about 20 to 100°C, preferably
5 50 to 90°C, may be used and may be a continuation of the polymerization of the aromatic core, or, in the alternative, may be carried out separately. Added emulsifiers, initiators, buffers and molecular weight regulators useful in the preparation of the core may be used in the stated amounts in the process for the preparation of the shell. The crosslinking agents used
10 in the making of the core are, in the above stated amounts, useful in preparing the crosslinked shell. Examples of such crosslinking agents are compounds having more than one non-conjugated double bond, such as, tri-allyl cyanurate, di-allyl maleate, di-vinyl benzene, ethylene glycol di-(meth)acrylate and butylene glycol di-methacrylate. Typically, these are
15 used in amounts of about 0.1 to 10%, preferably 0.5 to 3%, relative to the weight of the monomers used to prepare the elastomeric substrate or shell.

To prepare the grafted phases of the components (A) and (B), a monomer system containing at least one monomer selected from a first
20 group consisting of styrene, α -methyl styrene, ring-alkylated styrene, such as, p-methylstyrene and tert.butylstyrene, with at least one monomer selected from a second group consisting of (meth)acrylonitrile and methylmethacrylate (herein "SAN"), is polymerized in the presence of the latex of crosslinked rubber, preferably, acrylic acid ester polymer which in
25 the preferred embodiments contains about 1 to 25 percent relative to its weight of a polymer of vinyl aromatic monomer, preferably, styrene (core). The weight ratio between the monomer of said first group to said monomer of said second group is 80:20 to about 65:35.

It is advantageous if this graft copolymerization of the grafted phase
30 onto the crosslinked rubber substrate is carried out in aqueous emulsion

- 10 -

under the conventional conditions. The graft copolymerization may advantageously be carried out in the same system as the emulsion polymerization, which is used to prepare the substrate, optionally with the further addition of emulsifier and initiator. The monomer system to be

5 grafted onto the base, can be added to the reaction mixture all at once, in several stages or, preferably, continuously during the polymerization. The graft copolymerization of the mixture onto the crosslinked rubber substrate is conducted such that a degree of grafting of 10 to 50% by weight, preferably 20 to 40% by weight, in the grafted rubbers (A) and (B), results.

10 Since the grafting yield of the graft copolymerization is not 100%, it is necessary to employ a somewhat larger amount of the monomer mixture for the graft copolymerization than would correspond to the desired degree of grafting. The control of the grafting yield of the graft copolymerization, and, hence, the degree of grafting of the finished grafted rubbers (A) and

15 (B), is familiar to the art-skilled and is effected, inter alia, by the rate of addition of the monomers and by adding a molecular chain regulator (Chauvel and Daniel, ACS Polymer Preprints 15 (1974), 329 et seq.). The emulsion graft copolymerization, in general, produces about 10 to 25% by weight, based on the graft rubber, of free, non-grafted copolymer. The

20 proportion of the grafted rubber in the polymerization product obtained from the graft copolymerization is determined in accordance with the method specified above.

The grafted phase in the grafted rubbers (A) and (B), along with the non-grafted (free) polymer produced in the emulsion polymerization, is

25 recovered as dry solids from the liquid latex by the usual coagulation, washing, dewatering and drying techniques.

As discussed above, the composition, in accordance with the invention, contains as Component (D) a styrene copolymer which includes a copolymer of at least one monomer selected from a first group consisting

30 of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated

- 11 -

styrene and at least one monomer selected from a second group consisting of (meth)acrylonitrile, and methyl methacrylate. The weight ratio between said monomer(s) of said first group to said monomer(s) of said second group is 80:20 to about 65:35. The free, non-grafted copolymer
5 formed during the graft copolymerization, for the preparation of the components (A) and (B), may also form part of the hard component (D). Depending on the conditions selected for the graft copolymerization to prepare the grafted rubber component (A) and (B), it is practically inevitable that a proportion of component (D) has already been formed
10 during the graft copolymerization. In general, however, it is permissible to mix the products obtained from the graft copolymerization with additional, separately prepared component (D).

This additional, separately prepared, optional component (D) is preferably a styrene/acrylonitrile copolymer, an α -methyl styrene/-
15 acrylonitrile copolymer or a α -methyl styrene/styrene/acrylonitrile terpolymer. These copolymers can be employed individually, or as mixtures with one another, as component (D), so that the additional separately prepared hard component (D) of the composition, according to the invention, can be, for example, a mixture of a styrene/acrylonitrile
20 copolymer and a α -methyl styrene/acrylonitrile copolymer. Component (D) may be obtained by conventional methods. Thus, the copolymerization of styrene and/or α -methyl styrene with acrylonitrile can be carried out by radical polymerization preferably mass polymerization, solution polymerization, suspension polymerization or aqueous emulsion
25 polymerization.

The mixing of the components for the preparation of the inventive composition may be carried out conventionally by method and equipment well known in the art.

The composition may contain, as further components, any additive
30 conventionally used for their art recognized utility in thermoplastic molding

- 12 -

compositions, such as fillers, other compatible plastics, plasticizers, mold release agents, antistatic agents, antioxidants, lubricants, dyes, pigments, flame retarding agents, hydrolysis stabilizers and UV absorbers. The additives may be used in conventional effective amounts, preferably of
5 from 0.1 to a total of about 30% relative to the total weight of A + B + C + D.

The examples, which follow, illustrate the invention. In the examples, parts and percentages are by weight, unless stated otherwise.

EXAMPLES

10 Experimental:

Compositions representative of the invention have been prepared and their properties determined. The results of the determinations are shown in the table below. In the preparation of the compositions, the individual components used in the examples were as follows:

15 ASA -1: ASA rubber having a monomodal size distribution and a weight average particle size of 0.14 microns comprising a butyl acrylate substrate and a grafted SAN phase. The content of acrylonitrile (AN) in the grafted SAN was 30% relative to the weight of the grafted phase.

20 ASA -2: ASA rubber having a bimodal size distribution having a corresponding weight average particle sizes of 0.175 microns (small mode) and 0.375 microns (large mode).

The small mode comprises a grafted core-shell; the content of AN in the grafted S/AN was 22.5% relative to the weight of the grafted phase. The amount of styrenic core was 25% and the butyl acrylate rubber in the
25 core-shell structure amounted to 75% of the weight of the substrate.

The large mode comprises a grafted core-shell; the content of AN in the grafted S/AN was 20% relative to the weight of the grafted phase. The amount of styrenic core was 5% and the butyl acrylate rubber in the core-shell structure amounted to 95% of the weight of the substrate.

- 13 -

ASA-2 contained 50% of the small mode and 50% of the large mode, the percents being relative to the weight of ASA-2.

SAN: a styrene-acrylonitrile copolymer having acrylonitrile content of 32% relative to the weight of the copolymer.

5 PVC: polyvinyl chloride resin.

All compositions contained conventional additives for their art-recognized utility, believed to have no criticality in the present context.

Example	1	2	3	4
10 ASA-1	30	37.5	45	—
ASA-2	—	—	—	37.5
SAN	20	12.5	5	12.5
15 PVC	50	50	50	50
Properties				
20 Gloss, 75°	40	33	20	17
Bowing (inches)	0.4	0.7	1.7	0.4

Gloss values were determined in accordance with ASTM D 523
 25 using a Gardner Glossmeter at 75 degrees incident angle. The degree of bowing, an indication of dimensional stability is determined by placing a length of extruded profile on a flat surface. Bowing was measured as the distance between the flat surface and the profile at the extreme width of the profile. If the profile remains in contact with the flat surface at the
 30 extreme width of the profile, the bowing is zero.

The data (Comparative Examples 2 and 4) show that the reduced gloss and improved dimensional stability is a characteristic of the inventive composition and that these advantageous characteristics are not shared by a corresponding composition that is identical in all respects except for
 35 the monomodal size distribution of its ASA component.

- 14 -

Although the invention has been described in detail in the foregoing
for the purpose of illustration, it is to be understood that such detail is
solely for that purpose and that variations can be made therein by those
skilled in the art without departing from the spirit and scope of the
5 invention except as it may be limited by the claims.

- 15 -

WHAT IS CLAIMED IS:

1. A thermoplastic molding composition comprising
 - (A) a first grafted rubber having a weight average particle size of 0.05 to 0.30 microns,
 - 5 (B) a second grafted rubber having a weight average particle size of 0.31 to 1.00 microns,
 - (C) (co)polymer of vinyl chloride, and, optionally,
 - (D) styrene copolymer,wherein total rubber content is 15 to 25 percent relative to the total weight
10 of (A), (B) and (C) and (D) and wherein said grafted rubber, both occurrences, contains a grafted phase and a substrate, and wherein said grafted phase contains a copolymer of at least one monomer selected from a first group consisting of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated styrene and at least one monomer
15 selected from a second group consisting of (meth)acrylonitrile and methyl methacrylate, wherein weight ratio between said monomer of said first group and said monomer of said second group is about 80:20 to about 65:35 and wherein the substrate comprises the crosslinked polymerization product of at least one member selected from the group consisting of C₂₋₈-
20 alkyl acrylate, vinyl acetate, hydrogenated diene and diene, said styrene copolymer (D) containing a copolymer of at least one monomer selected from a first group consisting of styrene, α -methyl styrene, ring-halogenated styrene and ring-alkylated styrene and at least one monomer selected from a second group consisting of (meth)acrylonitrile and methyl
25 methacrylate where weight ratio between said monomer of said first group to said monomer of said second group ranges from 80:20 to about 65:35.
2. The thermoplastic molding composition of Claim 1 wherein particle size of said (A) is 0.10 to 0.25 microns.
3. The thermoplastic molding composition of Claim 1 wherein
30 particle size of said (B) is 0.32 to 0.60 microns.

- 16 -

4. The thermoplastic molding composition of Claim 1 wherein rubber content is 17 to 23 percent.

5. The thermoplastic molding composition of Claim 1 wherein the total amount of (A) and (B) is about 25 to 50 percent relative to the
5 total weight of A + B + C + D.

6. The thermoplastic molding composition of Claim 1 wherein the amount of (C) is about 25 to 75 percent relative to the total weight of A + B + C + D.

7. The thermoplastic molding composition of Claim 1 wherein
10 (A) and (B) are present in the composition at weight ratio of 9/1 to 1/9 therebetween.

8. The thermoplastic molding composition of Claim 1 wherein grafted phase and substrate are present at a weight ratio of 0.3 to 1 therebetween.

15 9. The thermoplastic molding composition of Claim 1 wherein substrate in at least one of said (A) and (B) comprise a core/shell structure.

10. The thermoplastic molding composition of Claim 9 wherein structure comprises (a) about 2 to 10% of a core containing at least one
20 vinylaromatic polymer, and (b) about 60 to 98% of a shell containing the crosslinked polymerization product of at least one member selected from the group consisting of C₂₋₈-alkyl acrylate, vinyl acetate, hydrogenated diene and diene, said percents being relative to the weight of said structure.

25

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/08937

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08L51/04 C08L55/02 C08L27/06 C08L33/08 C08F265/04
C08F279/02 C08F263/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08L C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 902 744 A (LINDNER CHRISTIAN ET AL) 20 February 1990 (1990-02-20) * claims 1-5 ; column 1, line 1 - column 2, line 41 ; column 3, line 5-16 ; examples *	1-8
X	US 5 274 031 A (EICHENAUER HERBERT ET AL) 28 December 1993 (1993-12-28) * column 5, line 6-10 ; claims 1-3 ; column 3, line 42 - column 4, line 6 ; column 3, line 11-41 ; examples * -/--	1-9

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

10 July 2001

Date of mailing of the international search report

19/07/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hammond, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/08937

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 534 212 A (BASF AG) 31 March 1993 (1993-03-31) cited in the application * page 9, line 20-24 ; claims 1-4 ; page 6, line 14-24 ; page 5, line 48 - page 6, line 11 ; page 11, line 16-34 * page 11, line 16-34 ----	1-10
X	EP 0 892 015 A (KANEKAFUCHI CHEMICAL IND) 20 January 1999 (1999-01-20) * claim 1 ; page 6, line 8-14 ; page 5, line 17-20 ; page 6, line 15-29 ; examples * ----	1-8
Y	US 5 932 655 A (CHANG MOH CHING OLIVER ET AL) 3 August 1999 (1999-08-03) cited in the application claims 1-10 ----	1-10
Y	US 4 778 850 A (LINDNER CHRISTIAN ET AL) 18 October 1988 (1988-10-18) claims 1-6 ----	1-10
A	US 3 670 052 A (SAITO KAZUO ET AL) 13 June 1972 (1972-06-13) abstract; claims 1-10 ----	1-10
A	DE 31 35 667 A (BASF AG) 17 March 1983 (1983-03-17) abstract; claims 1,2 -----	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

In: International Application No

PCT/US 01/08937

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4902744	A	20-02-1990	DE 3742103 A DE 3889874 D EP 0319848 A JP 1207347 A JP 2622408 B	22-06-1989 07-07-1994 14-06-1989 21-08-1989 18-06-1997
US 5274031	A	28-12-1993	DE 3839588 A DE 58903287 D EP 0370344 A JP 2185555 A	31-05-1990 25-02-1993 30-05-1990 19-07-1990
EP 0534212	A	31-03-1993	DE 4131728 A DE 59204581 D ES 2080402 T JP 5302009 A	25-03-1993 18-01-1996 01-02-1996 16-11-1993
EP 0892015	A	20-01-1999	US 6204327 B CA 2250732 A CN 1215418 A WO 9736959 A	20-03-2001 09-10-1997 28-04-1999 09-10-1997
US 5932655	A	03-08-1999	NONE	
US 4778850	A	18-10-1988	DE 3622736 A DE 3782212 A EP 0255594 A JP 1639825 C JP 3004581 B JP 63023948 A	07-01-1988 19-11-1992 10-02-1988 18-02-1992 23-01-1991 01-02-1988
US 3670052	A	13-06-1972	FR 1443820 A GB 1110963 A NL 6510625 A BE 675520 A DE 1569102 A FR 1457830 A GB 1086888 A NL 131621 C NL 6515486 A	21-09-1966 24-04-1968 26-07-1966 16-06-1966 29-10-1970 19-01-1967 11-10-1967 26-07-1966
DE 3135667	A	17-03-1983	NONE	